

**SKAMOL SUPER-1100 E calcium silicate insulating boards**  
for back-up insulation up to 1100°C (2012°F)



Grade	SUPER-1100 E	
<b>Maximum service temperature (EN 14306:2009)</b>		
	°C	1100
	°F	2012
<b>Bulk density, dry (EN 1094-4)</b>		
	kg/m <sup>3</sup>	245
	lbs/cu.ft.	15.3
<b>Compressive strength (EN 1094-5: 1995)</b>		
@ room temperature	MPa	2.7
	lbs/sq.in.	392
<b>Modulus of rupture (EN 993-6: 1995)</b>		
	MPa	1.3
	lbs/sq.in.	188.5
<b>Total porosity (EN 1094-4:1995)</b>		
	%	90
<b>Permeability to air (BS EN 993-4: 1995)</b>		
	nPm	0.5
<b>Creep in compression (EN 993-9: 1997)</b>		
50 h at 900°C (1652°F), load 0.1 MPa (14.5 lbs/sq.in.)	%	0.4
<b>Specific heat</b>		
	kJ/(kg×K)	0.84
	BTU/(lb×°F)	0.20
<b>Coefficient of reversible thermal expansion (BS 1902: section 5.3: 1990)</b>		
@ 20°C-750°C (68°F-1382°F)	K <sup>-1</sup>	5.5x10 <sup>-6</sup>
	°F <sup>-1</sup>	3.1x10 <sup>-6</sup>
<b>Linear reheat shrinkage (EN 1094-6: 1999)</b>		
12 h at 50°C (90°F) below max. service temp.	%	1.5
<b>Pyrometric cone equivalent (ASTM C24-89 ORTON cones)</b>		
	°C	1345
	°F	2453
<b>Thermal conductivity (ASTM C-182)</b>		
mean temp. @ 200°C	W/(m×K)	0.08
@ 400°C		0.10
@ 600°C		0.12
@ 800°C		0.14
@ 392°F	BTU/(sq.ft×h×°F/in)	0.55
@ 752°F		0.69
@ 1112°F		0.83
@ 1472°F		0.97
<b>Chemical analysis, typical</b>		
	%	
Silica	SiO <sub>2</sub>	47
Alumina	Al <sub>2</sub> O <sub>3</sub>	0.3
Ferric oxide	Fe <sub>2</sub> O <sub>3</sub>	0.3
Magnesium oxide	MgO	0.6
Calcium oxide	CaO	45
Sodium oxide	Na <sub>2</sub> O	0.1
Potassium oxide	K <sub>2</sub> O	0.1
Loss on ignition 1025°C (1877°F)	LOI	6
<b>Non-combustibility tests (EN 13501-1:2007 + A2:2009)</b>		
Classification	Class A2-s1,d0 non-combustible	
<b>HS Tariff number</b>		
(Harmonized Commodity Description and Coding System)	6806.90.00	
Colour	GREY	

Skamol A/S  
Østergade 58-60  
DK-7900 Nykøbing Mors  
Denmark  
Tel: +45 9772 1533  
Fax: +45 9772 4975  
insulation@skamol.dk

www.skamol.com

Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted.

October 2012